LiteCrete®

LIGHT WEIGHT BLOCK&




Material Datasheet

1300 Solid\Hollow LIGHTWEIGHT LiteCrete Block

STANDARD FINISH

Length

With LiteCrete Block range of Dense and Lightweight Aggregate Blocks by **environt**, you are assured to find the building solution you need. Our blocks can be used with confidence in a vide variety of internal and external applications. Our quality assures that LiteCrete Block units are of consistent and superior quality to meet the requirement of ASTM C-90.



Size available Solid \ Hollow Block (in mm)

Height

390 190		140		
Block Weights (kg)*		Weights (kg) Hollow Block		Weights (kg) Solid Block
Dry		7.5		13.2
3% Moisture Content			77	13.6

^{*}These figures are a national average and variations may occur geographically, please contact your nearest Sale Office for more precise block weight.

Product Specifications

LiteCrete® Block TO ASTM C-90

'Aggregate Concrete Masonry Units Category 1 (dense and light-weight aggregates)'

CATEGORY: AGGREGATE CONCRETE

MASONRY UNIT

DIMENSIONAL TOLERANCES: ±3.5mm

COMPRESSIVE STRENGTH: Mean 4.5 Mpa

REACTION TO FIRE: Class A1 (3.5 hours)

WATER ABSORPTION: 18-20 lbs/cft

WATER VAPOUR PERMEABILITY: NA

GROSS DRY DENSITY: 1300 kg/m3 NET DRY DENSITY: 1300 kg/m3 THERMAL CONDUCTIVITY: 0.5 W/mk

DURABILITY AGAINST

FREEZE-THAW: NA



Features and Benefits

- Designed to meet the requirements of the Building regulations
- Demonstrates a high level of performance in loadbearing and other structural applications
- Manufactured utilising lightweight aggregates for a lighter block
- Meets the requirements of the manual handling regulations
- Open textured finish provides an excellent medium for surface finishes and fixings
- Inherent light weight limits heat loss through external walls